



9497498415 | 16 | 17

ANSWER KEY

QUIZ NO: 840

TOPIC: CONCRETE TECHNOLOGY

DATE: 02/07/2024

- 1. Increase in fineness modulus of aggregate indicates
- [A] Finer grading
- [B] Coarser grading
- [C] Gap grading
- [D] None of the above

Answer: B

- 2. Adding a thin layer of cement mortar to the surface of concrete:
- [A] Laitance
- [B] Quartering
- [C] Retempering
- [D] Rendering

Answer: D





9497498415

ANSWER KEY

3.	Bulking	of sand	caused	due	to
----	----------------	---------	--------	-----	----

- [A] Surface moisture
- [B] Viscosity
- [C] Air in voids
- [D] Silt present

Answer: A

4. Instrument used for determining the soundness of cement is:

- [A] Le Chatelier apparatus
- [B] Wagner's turbidimeter
- [C] Vicat apparatus
- [D] None of the above

Answer: A

5. Low heat cement is preferred for:

- [A] Slabs
- [B] Columns
- [C] Dams
- [D] Foundation

Answer: C





9497498415 | 16 | 17

ANSWER KEY

6.	Slump test is performed in concrete mix to determine the: [A] Workability
	[B] Water content
	[C] Strength
	[D] Durability
	Answer: A
7.	The property of increase in volume of fine aggregate due to moisture is
	called:
	[A] Slacking
	[B] Bulking
	[C] Warping
	[D] Shrinking
	Answer: B
8.	For masonry work with solid bricks consistency of mortar should be:
	[A] 5 to 8 cm
	[B] 9 to 13 cm
	[C] 14 to 18 cm

[D] 19 to 23 cm

Answer: B





9497498415 | 16 | 17

ANSWER KEY

- 9. A compound which is added to concrete to reduce the setting time of concrete:
- [A] Air entraining agent
- [B] Accelerators
- [C] Plasticizers
- [D] None of the above

Answer: B

- 10. To prevent segregation, the concrete should not be thrown from a height of more than:
- [A] 0.5 m
- [B] 1 m
- [C] 1.5 m
- [D] 2 m

Answer: C

Join our social media platforms









